



25 FT. (7.6m) PACK WITH SHEARS * PART NO.	100 FT. (30.5m) REEL PART NO.	"W"	"T" APPLICATION THICKNESS
MCCG-1N-PK	MCCG-1N	.19 (4.8)	.029-.045 (0.7-1.1)
MCCG-2N-PK	MCCG-2N		.044-.056 (1.1-1.4)
MCCG-3N-PK	MCCG-3N		.055-.069 (1.4-1.7)
MCCG-4N-PK	MCCG-4N	.23 (5.8)	.069-.090 (1.7-2.3)
MCCG-6N-PK	MCCG-6N		.113-.130 (2.9-3.3)

NOTES:

1. MATERIAL: 304 STAINLESS STEEL (RMS-283).
2. COATING: NYLON 11 (RMS-192), COLOR: BLACK.
3. CUSHION: THERMOPLASTIC ELASTOMER, 60 SHORE D (RMS-300), COLOR: BLACK.  
TABER ABRASION RESISTANCE: PER D1044 1kg LOAD, C17 WHEEL, 25 mg LOSS AFTER 1000 CYCLES.
4. DIELECTRIC STRENGTH: 1500 VOLTS @ 60 HZ.
5. OPERATING TEMPERATURE RANGE: -40°F TO 185°F (-40°C TO 85°C).
6. SALT SPRAY TESTING: 2000 HOURS, ASTM B117. MIL-STD-202, METHOD 301.
7. FLAMMABILITY: UL 94 V-0 YELLOW CARD NO. E113553 NZMT2.
8. RANDOM SHOCK AND VIBRATION: MIL-STD-1344, METHOD 2005.1, TEST CONDITION VI, LETTER "J".  
DURATION 8 HOURS LONGITUDINAL AND 8 HOURS PERPENDICULAR. rms G 41.7.
9. HAND HELD CUTTING TOOL NEEDED, ORDER P/N : MCGS-1
10. FITS ANY TWO AXIS CONTOUR.
11. COLOR CODE STRIPE: PRINTING INK (RMS-346).

TITLE: METAL CONTINUOUS CUSHION GROMMET			DWG IN IN(MM)		FINAL		
C	SEE ECN #1284 FOR CHANGES	SK 02.08.07	FILE # MCCG	DWN: E.P.	APP:	PART # SEE TABLE	PRINT TYPE CA
B	SEE ECN #1283 FOR CHANGES	SK 02.05.07	MAT'L: SEE NOTES	DT: 11-9-98	DT:		
A	ADDED "POLYESTER..." TO NOTE 2. REMOVED NOTE 5. & CHANGED FILE NO.	SM 09.18.01	RE: RICHCO, INC.	RICHCO INC. PO BOX 804238, CHICAGO, 60680 (773) 539-4060			
REV	DESCRIPTION	ENGR DATE	TOLERANCES UNLESS NOTED .XX=±.010 .XXX=±.005 FRAC=±1/64 ANG=±1'				